

TEST REPORT

REPORT NO.: 2017FE0044	PAGE 1 OF 5
-------------------------------	---------------------------

This Test Report refers only to samples submitted by the applicant to SIRIM QAS International Sdn. Bhd. and tested by SIRIM QAS International Sdn. Bhd. This Test Report shall not be reproduced, except in full and shall not be used for any purpose by any means or forms (including but not limited to advertising purposes) without written approval from the Managing Director, SIRIM QAS International Sdn. Bhd. Please refer overleaf of Page 1 for Conditions Relating to the Use of Test Report.

Applicant/ Manufacturer : **EASY WOOD SDN. BHD.**
 No. 4, Jalan BP 5/8,
 Bandar Bukit Puchong,
 47100 Puchong,
 Selangor Darul Ehsan.
(Attn: Mr. Ben Fok / Mr. Mike Ng)

Product : **EAZY WOOD VINYL COMPOSITE TONGUE & GROOVE CEILING STRIP & WALL PANEL #1**

Reference Standard/ Method of Test : BS 476: Part 6: 1989+A1:2009
 Fire Test on Building Materials and Structures
 Part 6: Method of Test for Fire Propagation for Products.

Description of Test Specimen : 6 pieces of Eazy Wood Vinyl Composite Tongue & Groove Ceiling Strip & Wall Panel #1.
 Size of Specimen : 225mm x 225mm x thickness (Refer to page 2)
 Brand : EAZY WOOD
 Mass Per Unit Area : 4.02 kg/m²

Descriptions of sample as claimed by the submitter: Refer to page 2


The specimens were tested with the face side exposed to the specified heating condition of the fire test.

Date Received : 24.11.2016
Date of Test : 11.01.2017
Job No./ Ref No. : J20161440620 /SQAS/FPS/15/1-5

Test Result :	Subindex i1	Subindex i2	Subindex i3	Fire Propagation Index (I)
	3.1	6.3	1.5	10.9

Issued Date : 17 MAR 2017

Approved Signatories :



MUHAMMAD SAFUAN MUSA
 Testing Executive






ROHAYA IBRAHIM
 Head
 Fire Protection Section
 Testing Services Department
 SIRIM QAS International Sdn. Bhd.

This Test Report refers only to samples submitted by the applicant to SIRIM QAS International Sdn. Bhd. and tested by SIRIM QAS International Sdn. Bhd. This Test Report shall not be reproduced, except in full and shall not be used for any purpose by any means or forms (including but not limited to advertising purposes) without written approval from the Managing Director, SIRIM QAS International Sdn. Bhd. Please refer overleaf of Page 1 for Conditions Relating to the Use of Test Report.

Descriptions of sample as claimed by the submitter:



Eazy Wood Vinyl Composite Tongue & Groove
Ceiling Strip & Wall Panel #1



[Handwritten signature]

17 MAR 2017

This Test Report refers only to samples submitted by the applicant to SIRIM QAS International Sdn. Bhd. and tested by SIRIM QAS International Sdn. Bhd. This Test Report shall not be reproduced, except in full and shall not be used for any purpose by any means or forms (including but not limited to advertising purposes) without written approval from the Managing Director, SIRIM QAS International Sdn. Bhd. Please refer overleaf of Page 1 for Conditions Relating to the Use of Test Report.

Product : EAZY WOOD VINYL COMPOSITE TONGUE & GROOVE CEILING STRIP & WALL PANEL #1
 Brand : EAZY WOOD Mass Per Unit Area : 4.02 kg/m²
 Date of Test : 11.01.2017

Time (Min.)	Temperature Rise Above Ambient (°C)				
	Calibration	Specimen A	Specimen B	Specimen C	Specimen Average
0.5	13	16	14	15	15
1.0	17	22	22	23	22
1.5	21	30	28	30	29
2.0	23	32	33	36	33
2.5	25	38	37	39	38
3.0	29	42	41	44	42
4.0	57	86	86	89	87
5.0	92	137	137	137	137
6.0	120	189	191	181	187
7.0	143	219	219	217	218
8.0	162	240	244	239	241
9.0	178	250	252	252	251
10.0	190	253	259	262	258
12.0	204	270	268	268	268
14.0	220	267	279	280	275
16.0	231	267	275	282	274
18.0	240	277	268	278	274
20.0	244	275	264	274	271
Subindex 1		3.1	2.6	3.5	3.1
Subindex 2		6.3	6.4	6.3	6.3
Subindex 3		1.5	1.5	1.6	1.5
Index of Performance		10.9	10.5	11.4	10.9



[Handwritten signature]

17 MAR 2017

This Test Report refers only to samples submitted by the applicant to SIRIM QAS International Sdn. Bhd. and tested by SIRIM QAS International Sdn. Bhd. This Test Report shall not be reproduced, except in full and shall not be used for any purpose by any means or forms (including but not limited to advertising purposes) without written approval from the Managing Director, SIRIM QAS International Sdn. Bhd. Please refer overleaf of Page 1 for Conditions Relating to the Use of Test Report.

Date of Test : 11.01.2017

No. of Specimen Tested : 3 nos.

The Fire Propagation Index **I** is **10.9** for the Eazy Wood Vinyl Composite Tongue & Groove Ceiling Strip & Wall Panel #1 with mass per unit area of 4.02 kg/m².

The Subindex i1 is 3.1

The Subindex i2 is 6.3

The Subindex i3 is 1.5


The test results relate only to the behavior of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.



17 MAR 2017

This Test Report refers only to samples submitted by the applicant to SIRIM QAS International Sdn. Bhd. and tested by SIRIM QAS International Sdn. Bhd. This Test Report shall not be reproduced, except in full and shall not be used for any purpose by any means or forms (including but not limited to advertising purposes) without written approval from the Managing Director, SIRIM QAS International Sdn. Bhd. Please refer overleaf of Page 1 for Conditions Relating to the Use of Test Report.

Product : EAZY WOOD VINYL COMPOSITE TONGUE & GROOVE CEILING STRIP & WALL PANEL #1
 Brand : EAZY WOOD Mass Per Unit Area : 4.02 kg/m²
 Date of Test : 11.01.2017



[Handwritten signature]

17 MAR 2017